

Revised
January 2003



9411 Corsair Road
Frankfort, IL 60423
1-800-552-0299 Phone
1-815-464-5650 Fax

EMERGENCY PHONE 1-800-255-3924
TECHNICAL DATA SHEETS
MG 5

Description:

MG5 is a medical grade instant adhesive. These products have USP Class VI certification and are used in assembling medical devices.

Physical Properties:

COLOR: Clear
VISCOSITY: 5 cps
BASE: Ethyl
STRENGTH: 2700/4300
TEMPERATURE RANGE: - 65 - 200°F
CURE SPEED: 15 seconds
(FIXTURE)
FULL CURE: 8 hours
MIL A 46050 Type II
Class I
SPECIFIC GRAVITY 1.05
SOLUBLE IN: Remove Debonder

Storage

The MG series is ideally stored in a cold, dry location in unopened containers. Optimal storage temperature is under 50°F. To prevent contamination of unused product, do not return any material to its original container.

Handling Characteristics:

Shear Strength, ASTM D1002, DIN 53283	Value	Range
Grit Blasted Steel, N/mm ² (psi)	23 (3250)	20 to 28 (2910 to 3970)
Etched Aluminum, N/mm ² (psi)	17 (2450)	13 to 22 (1950 to 3125)
ABS, N/mm ² * (psi)	>7 (>885)	
PVC, N/mm ² * (psi)	>7 (>890)	
Polycarbonate, N/mm ² * (psi)	>6 (>825)	
Phenolic, N/mm ² * (psi)	12 (160)	6 to 18 (775 to 2450)
Neoprene rubber, N/mm ² * (psi)	>12 (>1600)	
Nitrile rubber, N/mm ² * (psi)	>12 (>1600)	
Tensile Strength, ASTM D2095, DIN 53283		
Grit Blasted Steel, N/mm ² (psi)	20 (3000)	14 to 28 (1900 to 4000)

* Substrate Failure

Engineering Excellence

For technical information
and support call **1-800-552-0299** or visit our website at

www.instantca.com